

HYOSUNG Polypropylene The Next Circular Economy

F801C

Polypropylene Homopolymer For Extrusion Coating Applications

Product Description

Hyosung Polypropylene F801C is a Homo polypropylene manufactured by under the Spheripol process. This grade is designed to potential and use applications include Extrusion coating on woven and kraft paper. It exhibits low neck-in, high speed processability and good adhesive property to paper, oil & moisture permeation resistance. This grade is designed to potential end use applications include Extrusion coating on Woven and Kraft paper.

Characteristics

Typical Application PP woven bag, Resin, fish, steel tube, dog food packaging

Features Low neck-in / High speed processability / Good adhesive property / Oil resistance

Typical Properties

Characteristics	Method	Value	Unit
Physical			
Melt Index (230°C, 2.16kg)	ASTM D1238	25.0	g/10min
Density	ASTM D792	ASTM D792 0.90	
Mechanical			
Tensile Strength at Yield	ASTM D638	340	kg/m²
Flexural Modulus	ASTM D790	14,000	kg/m²
Notched Izod Impact Strength (23°C)	ASTM D256	3.5	kg·cm/cm
Rockwell Hardness	ASTM D785	95	R-scale

The values listed above are typical values for reference purpose only and shall not be construed as specifications.

Contacts

Head Office Lot 01CN ~ 08CN, Cai Mep Industrial Park,

Tan Phuoc Ward, Phu My City, Ba Ria Vung Tau

Province, Vietnam.

Tel: +84-254-393-7949 Fax: +84-254-393-7849

Online www.hyosungchemical.com

www.hyosungvinachemicals.com










TECHNICAL DATA SHEET HYOSUNG VINA CHEMICALS

HYOSUNG Polypropylene The Next Circular Economy

F801C

Polypropylene Homopolymer For Extrusion Coating Applications

Processing Conditions



Specifications	Unit	Recommended Conditions
Die Temperature	°C	290 ~ 300
Nozzle Temperature	°C	290 ~ 300
Front Temperature	°C	285 ~ 295
Middle Temperature	°C	240 ~ 250
Rear Temperature	°C	200 ~ 210

Considerations

Due to variations in screw design and heat efficiency according to types of facilities, optimal conditions for each facility may differ. Therefore, the optimal temperature conditions for each facility must be taken into consideration depending on extruding pressure, cooling efficiency, changes in MI of the final product, appearances of the final product, etc.

Contacts

Head Office Lot 01CN ~ 08CN, Cai Mep Industrial Park,

Tan Phuoc Ward, Phu My City, Ba Ria Vung Tau

Province, Vietnam.

Tel: +84-254-393-7949 Fax: +84-254-393-7849

Online www.hyosungchemical.com

www.hyosungvinachemicals.com











HYOSUNG Polypropylene The Next Circular Economy

F801C

Polypropylene Homopolymer For Extrusion Coating Applications

Health, Safety and Food Contact Regulations

Hyosung Polypropylene F801C complies with FDA requirements in the code of Federal Regulations in 21 CFR 177. 1520 for food contact and European Commission Regulation (EU) No 10/2011 and its amendment (EU) No 2016 / 1416 with regard to plastic materials and articles intended to come into contact with food.

Storage and Handling

This product should be stored in dry condition at temperature below 40°C and protected from UV-light. When condensation is visible or can be expected, pre-drying is recommended. (Drying condition: 80~100°C/2~4hours at air circulated condition).

Disclaimer

All information, including product characteristics, applications and properties are for reference purpose only and shall not be construed as specifications. Before using this product, customers should carefully review the instructions for use of the product to determine whether the product is suitable for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of this product. HYOSUNG VINA CHEMICALS CORPORATION assumes no legal responsibility or liability for the contents of this document. We reserve the right to change the contents of this document without prior notice. This document is copyrighted by HYOSUNG VINA CHEMICALS CORPORATION.

Contacts

Head Office Lot 01CN ~ 08CN, Cai Mep Industrial Park,

Tan Phuoc Ward, Phu My City, Ba Ria Vung Tau

Province, Vietnam.

Tel: +84-254-393-7949 Fax: +84-254-393-7849

Online www.hyosungchemical.com

www.hyosungvinachemicals.com







