

M6000NR

Polypropylene Random Terpolymer
 For Metallizing CPP Film

Product Description

Hyosung Polypropylene M6000NR is a polypropylene random terpolymer that features excellent transparency and gloss. It has a very low haze and a low SIT (Seal Initiation Temperature). It is suitable for sealant of metallizing CPP film and package for food and cosmetics.

Hyosung Polypropylene M6000NR contains no film additives like slip and anti-blocking agents.

Characteristics

Typical Application Sealant of metallizing CPP film / Package for food and cosmetics.

Features Excellent transparency / Low SIT (Seal Initiation Temperature) / Excellent heat seal property.

Typical Properties

Characteristics	Method	Value	Unit
Physical			
Melt Index (230°C, 2.16kg)	ASTM D1238	7.0	g/10min
Density	ASTM D792	0.90	g/cm ³
Mechanical			
Tensile Strength at Yield	ASTM D638	250	kg/cm ²
Flexural Modulus	ASTM D790	8,000	kg/cm ²
Notched Izod Impact Strength (23°C)	ASTM D256	7.0	kg·cm/cm
Rockwell Hardness	ASTM D785	85	R-scale
Thermal			
Melting Temperature	HS Method	130	°C
Heat Seal Temperature	HS Method	119	°C
Heat Seal Initiation Temperature	HS Method	105	°C

The values listed above are typical values for reference purpose only and shall not be construed as specifications.

Contacts

Head Office

Lot 01CN ~ 08CN, Cai Mep Industrial Park,
 Tan Phuoc Ward, Phu My City, Ba Ria Vung Tau
 Province, Vietnam.

Tel: +84-254-393-7949 Fax: +84-254-393-7849

Online

www.hyosungchemical.com
www.hyosungvinachemicals.com



M6000NR

Polypropylene Random Terpolymer
For Metallizing CPP Film

Health, Safety and Food Contact Regulations

Hyosung Polypropylene M6000NR complies with FDA requirements in the code of Federal Regulations in 21 CFR 177. 1520 for food contact and European Commission Regulation (EU) No 10/2011 and its amendment (EU) No 2016 / 1416 with regard to plastic materials and articles intended to come into contact with food.

Storage and Handling

This product should be stored in dry condition at temperature below 40°C and protected from UV-light. When condensation is visible or can be expected, pre-drying is recommended. (Drying condition: 80~100°C/2~4hours at air circulated condition).

Disclaimer

All information, including product characteristics, applications and properties are for reference purpose only and shall not be construed as specifications. Before using this product, customers should carefully review the instructions for use of the product to determine whether the product is suitable for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of this product. HYOSUNG VINA CHEMICALS CORPORATION assumes no legal responsibility or liability for the contents of this document. We reserve the right to change the contents of this document without prior notice. This document is copyrighted by HYOSUNG VINA CHEMICALS CORPORATION.

Contacts

Head Office

Lot 01CN ~ 08CN, Cai Mep Industrial Park,
Tan Phuoc Ward, Phu My City, Ba Ria Vung Tau
Province, Vietnam.

Tel: +84-254-393-7949 Fax: +84-254-393-7849

Online

www.hyosungchemical.com
www.hyosungvinachemicals.com

